




INDUSTRIAL ENERGY PRODUCTS

phone: (717) 492-1853
fax: (717) 492-1856
email: info@iepindustrial.com



Making Aircraft Quieter, Safer and More Comfortable.
5000 North Highway 251, Davis Junction, IL 61020 | 800 945 7135 | www.skandiainc.com

VERTICAL FLAMMABILITY TEST RESULTS				Skandia, Inc. WO # 254986-13			
14 CFR Part 25.853 (a) Amdt 25-116 Appendix F Part I (a)(1)(i) Amdt 25-117				Client PO Verbal			
Industrial Energy Products, Inc 56 Newcomer Road Mount Joy PA 17552 USA				Doc ID: 60-277692 Test Plan # Rev Technician Ryerson Rickey			
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION							
Make: Stock		Model: N/A		Serial: N/A		Tail: N/A	
Conditioning Room Data: Date In: 04/18/2013 Time In: 10:30				Date Out: 04/19/2013 Time Out: 13:20			
SPECIMEN MATERIALS							
Part No: HOT-STOP 'L' Fire Containment Bag Industrial Energy Products, Inc.: Brownish/ Red Lot No 4-17-13							
Set	Flame Application (seconds)	Flame Time (seconds)		Burn Length (inches)		Drip Flame Time (seconds)	
		Warp	Fill	Warp	Fill	Warp	Fill
1	60	0.0	0.0	2.3	2.3	0.0	0.0
2	60	0.0	0.0	2.9	2.3	0.0	0.0
3	60	0.0	0.0	3.0	2.3	0.0	0.0
Average:		0.0	0.0	2.7	2.3	0.0	0.0
<i>Vertical (60 second) Burn Test: Average Self-Extinguish time may not exceed 15 seconds. Average Burn Length may not exceed 6 inches. Average Dripping may not exceed 3 seconds after falling.</i>							
Comments:							
<input checked="" type="checkbox"/> Passed <input type="checkbox"/> Failed							
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.							
Judy Johnson - FAA DER WITNESS 						04/19/2013 DATE	